

Why do Thin Polymer Films Melt at Lower Temperature? A Continuum Approach

R. Seemann, K. Jacobs, and S. Herminghaus

Dept. of Applied Physics, University of Ulm, D-89069 Ulm, Germany

(February 1, 2008)

We have investigated the reduction of the glass transition temperature, T_g , for thin supported films of particularly small molecular weight ($M_W = 2$ kg/mol) polystyrene, and found good agreement with earlier studies on larger molecules. By combining the eigenmodes of the films with mode coupling theory, we arrive at a simple and predictive model which is in quantitative agreement with the data. Its *only fitting parameter* is the shear modulus governing the relevant fluctuations. The weak dependence of the latter upon the molecular weight of the polymer is in accordance with the general observation that the reduction of T_g is largely independent of chain length at sufficiently low molecular weight.

The experimental observation that thin polymer films melt at temperatures well below the glass transition temperature of the bulk polymer [1] is one of the major current challenges in the theory of homopolymers. Although one might at first glance expect such a behaviour, due to the impact of the finite size geometry of a thin film upon objects as large as polymer molecules, a slightly closer look reveals the intricacy of the problem: the effect of a noticeable reduction of the glass temperature T_g , namely, occurs in many cases at film thicknesses orders of magnitude larger than the end-to-end distance, R_{ee} , of the molecules. A fundamental understanding of this effect would be of great interest not only for polymer physics, but potentially also elucidate the physics of the glass transition in general.

For the sake of clarity, but without loss of sufficient generality, let us restrict our discussion to the case of polystyrene (PS), which is among the best studied polymers in this context. As it has recently been pointed out in very thorough and elucidating studies [2,3], it is necessary to distinguish between long chain polymers with molecular weight above about 380 kg/mol, and shorter ones. For long PS chains, with a molecular weight of, say, 500 kg/mol, a substantial reduction is observed at a thickness below approximately 60 nm. Although R_{ee} is still less than that, the length of a stretched molecule of this weight is of the order of one micron. In this case, the effect might indeed be attributed to finite size effects upon the chain conformation and chain motion. These ideas have been meanwhile developed and seem to reproduce successfully the features experimentally observed [4,5].

For shorter chains, however, the puzzle is more in-

volved, since it is meanwhile accepted that the characteristic dependence $T_g(h)$ upon the thickness is largely independent of the chain length [3,6] in this case. A finite size effect upon the geometry and motion of the single chain is thus ruled out as the basic mechanism. Many attempts have been undertaken to explain these findings on other grounds, mostly by considering microscopic models of the inner structure of the films. D. Long and F. Lequeux have envisaged the freezing of the film as a percolation of rigid domains [7], mediated by thermal fluctuations [8]. Other models assume a layered structure of the film, with a particularly mobile region close to the free surface of the film. Within this framework, Forrest and Mattsson [6] have recently been able to achieve quite impressive accordance with the experimental data [2,6]. Their model makes use of the so-called cooperativity length, $\xi(T)$, which plays a mayor role in a whole class of theoretical concepts of the glass transition. The only drawback is that there is yet no well established theory of $\xi(T)$. Furthermore, as a consequence of the two-layer structure of the film inherent in the model, it is not completely clear why there should not be two glass transitions rather than a single one shifted in temperature.

As a complementary approach, computer simulations of polymer films with free surfaces have recently been carried out, and most of the experimental findings were obtained qualitatively [9]. However, the polymer chains in these simulations were very much shorter than those used in the experiments (16 monomer units), well below the entanglement limit. It is therefore worthwhile to study experimentally the behaviour of polymers with short chain length, both to ease comparison with simulation and to explore the range of validity of the apparent independence of the shift of T_g on molecular weight.

We have thus investigated the glass transition in thin supported films of PS with a molecular weight as small as 2 kg/mol (≈ 20 monomer units). The polymer was purchased from Polymer Labs (UK) with a polydispersity index $M_W/M_N = 1.05$, the radius of gyration is 1.3 nm. Effects from the molecular geometry are thus expected only for films of few nanometers thickness. The films were spin cast from toluene solution onto silicon wafers (Silchem GmbH, Freiberg/Germany), which were previously cleaned by ultrasonication in acetone, ethanol, and toluene, subsequently. Residual organics were removed with Caro's acid (1:1 $H_2SO_4 + H_2O_2$), and the substrates were thoroughly rinsed with hot millipore water afterwards. Films were investigated with thicknesses ranging from 4 to 160 nm. The roughness of the free

surface of the films was less than 0.2 nm, as revealed by scanning force microscopy (SFM).

The glass transition temperature was determined in several ways independently. The standard procedure of monitoring the thermal expansion of the film via ellipsometry, as introduced by Keddy and Jones [1], was used for film thicknesses down to 9.6 nm. Thermal expansion coefficients agreed well with previously published data both above and below T_g . Possible loss of material during the heating and cooling procedures was checked by applying the Clausius-Mosotti relation to the thickness and refractive index data obtained from the ellipsometry. Perfect conservation of material was invariably found. At large film thickness, T_g obtained in this way approached 327 ± 1 K, which is consistent with the temperature at which macroscopic melting is observed in the bulk (T_g^0) for PS with this chain length.

For thinner films, we observed the buildup of amplified thermal fluctuations (spinodal dewetting) [10,11]. These processes were monitored by SFM with *in-situ* heating. In order to speed up the experiments to a feasible time scale, dewetting was observed at temperatures close to T_g^0 . In this way, the viscosity $\eta(T)$ was determined. Furthermore, we found that $\eta(T)$ varied with temperature according to a Vogel-Fulcher law, just as the bulk viscosity, but with the Vogel-Fulcher temperature shifted by a certain amount depending on film thickness. In this way, the apparent glass transition temperature of the film could be obtained by extrapolation.

Our data are shown in fig. 1 as the full symbols. The circles represent the thermal expansion measurements, the squares were obtained by extrapolation from spinodal dewetting experiments. As one can clearly see, the glass transition temperature is substantially reduced for all films thinner than about 50 nm. The solid line represents the function

$$T_g = T_g^0(1 + h_0/h)^{-1} \quad (1)$$

This form has been shown before to account well for the data obtained by others for larger molecular weight films, if $h_0 = 0.68$ nm was assumed for PS [12]. Within experimental scattering, our data exhibit indeed the same dependence of $T_g(h)$ in the full range of film thickness explored. Although our polymer chains are roughly by a factor of 50 shorter, we obtain $h_0 = 0.82$ from the fit, which is quite close to the above value. This confirms the weak dependence (if there is a significant one at all) of the reduction of the glass transition temperature on the molecular weight of the polymer, down to a molecular weight as small as 2 kg/mol, comparable to what has been studied by computer simulation [9].

It is clear that the behaviour displayed in fig. 1 can in no way be attributed to the geometrical impact of the finite film thickness upon the microscopic conformation of the individual chains. Were therefore present here a

novel approach to the problem which intentionally makes no reference to the molecular structure of the film. Inspired by the ‘melting’ of the spinodal waves, we consider instead the eigenmode spectrum of the (viscoelastic) polymer film. This can be considered with all possible boundary conditions at the substrate, such that films with large extrapolation length, or free standing films, may as well be treated within the same framework.

The spectrum can be obtained in a straightforward manner by combining standard theory of elasticity [13] and hydrodynamics [14] in the limit of small Reynolds number (Stokes dynamics). The equation of motion reads

$$\{\partial_t + \omega_0 + \frac{E}{\eta}\} \nabla^2 \phi = \frac{\nabla p}{\eta} \quad (2)$$

where E is Young’s modulus, η is the viscosity, and ω_0 is the rate of relaxation of the individual chains by diffusion. ϕ is a vector field related to the strain tensor, $\mathbf{S}$. If we restrict ourselves to one lateral (x) and one normal (z) coordinate, ϕ is defined via

$$\mathbf{S} = \begin{pmatrix} \partial_x \phi_x & \frac{1}{2}(\partial_x \phi_z + \partial_z \phi_x) \\ \frac{1}{2}(\partial_x \phi_z + \partial_z \phi_x) & \partial_z \phi_z \end{pmatrix} \quad (3)$$

Finally, p is the pressure field.

For harmonic excursions of the free surface, $\zeta(x) = \zeta_0 \exp\{iqx - \omega t\}$, eq.(2) has solutions of the type

$$\begin{aligned} \phi_x &= [1 + (h + q^{-1})\alpha(q)] \cosh qz - q^{-1}\alpha(q) \sinh qz \\ \phi_z &= [1 + h\alpha(q)] \sinh qz - z\alpha(q) \cosh qz \end{aligned} \quad (4)$$

where for the function $\alpha(q)$, we find

$$\alpha(q) = \left(\frac{q}{2}\right) \frac{e^{2qh} - 1}{e^{2qh} - 1 + qh} \quad (5)$$

for free standing films (symmetric modes) as well as for supported films with full slippage. At the free surface, we used the boundary conditions of zero tangential stress and $p = -\sigma \partial_{xx} \zeta$, where σ is the surface tension of the polymer. For free standing films, h is defined here as *half* the film thickness, such that the form of eqs. (4) and (5) accords with the experimental observation that the shift of T_g for a free film of thickness $2h$ is roughly the same as for a supported film of thickness h [15].

For the relaxation rates of the modes, we get

$$\begin{aligned} 2\omega &= (\omega_0 + \frac{E}{\eta} + \frac{\sigma q^2}{2\eta\alpha(q)}) \\ &\pm \sqrt{(\omega_0 + \frac{E}{\eta} + \frac{\sigma q^2}{2\eta\alpha(q)})^2 + \omega_0^2 \frac{2\sigma q^2}{\eta\alpha(q)}} \end{aligned} \quad (6)$$

As it will become clear below, it is mostly the high frequency modes which contribute appreciably to the reduction of the glass transition temperature. We thus consider only the high frequency branch of eq. (6). Since $\omega_0 \ll \frac{E}{\eta}$, the latter is approximately given by

$$\omega = \omega_0 + \frac{E}{\eta} + \frac{\sigma q^2}{2\eta\alpha(q)} \quad (7)$$

which is monotonously increasing with q . However, modes with q much larger than the inverse film thickness, h^{-1} , do not penetrate appreciably into the film, such that only a small fraction of the material takes part in these modes. Hence we are led to considering chiefly those modes for which $q \approx h^{-1}$, since these are the highest frequency modes comprising more or less all of the film material.

The central assumption is now that the physical cause for the melting, or freezing, of these thin film modes are *memory effects* in the polymer material. These are of course not included in the above linear theory, and may be formulated in a generic way by means of a suitable memory kernel, which may be written as $m\{\phi(t)\} = a_1\phi + a_2\phi^2 + a_3\phi^3 + \dots$ [16,17]. It should be well noted that we are considering the strain field, ϕ , which describes the local state of the material. The equation of motion (2) is of first order in time, hence we have

$$\phi' + \omega\phi + \lambda \int_0^t m\{\phi(\tau)\}\phi'(t-\tau)d\tau = 0 \quad (8)$$

where λ is a coupling parameter. This type of mode coupling equations has been thoroughly analysed [18] in relation to the *microscopic* physics of the glass transition (to which we do not refer here), as well as to large scale degrees of freedom [19]. It was found that the coefficients a_i of the memory kernel vary concurrently with temperature, and that upon crossing a certain border in the space spanned by the a_i , the system freezes into a nonergodic state [17]. The existence of such a freezing transition has been found to be largely independent of the precise form of the memory kernel. For the simple scaling analysis to be done here, we therefore simply assume the a_i to vary all in the same way, which appears to be justified closely enough to the transition. In what follows, we thus assume that all temperature dependence may be absorbed into the coupling parameter, λ , and the system freezes when a critical value, λ_c , is reached.

From eq. 8 we see directly that λ has the same dimension as ω , and there is no further independent time scale in the system. Since we expect $\lambda \rightarrow 0$ for $T \rightarrow \infty$, and $\lambda \rightarrow \infty$ for $T \rightarrow 0$, we can expand $\lambda = b_1 \frac{T_c}{T} + b_2 (\frac{T_c}{T})^2 + \dots$, with $\Sigma b_i = \lambda_c$. Retaining only the leading term [20], and setting $q = 1/h$ as discussed above, we arrive at a simple formula for the glass transition temperature:

$$T_g(D) = T_g^0 \left(1 + \frac{1.16 \sigma}{h(E + \eta\omega_0)} \right)^{-1} \quad (9)$$

This is exactly the form of eq. (1), and fig. 1 shows that this describes our data very well. There was no significant improvement by including higher terms in the expansion series for λ .

The quantity $\eta\omega_0$ is on the order of a few kPa and can in general be safely neglected against E . The characteristic length scale which appears here, and which was called h_0 in eq. (1), is thus the ratio σ/E , with the surface tension $\sigma = 31$ mN/m for PS. It should thus be well noted that the elastic modulus determining the dynamics of the relevant modes, E , is the only physical fitting parameter in the model.

The physical picture which emerges from this model is that as the temperature is increased, melting proceeds as the fastest mode involving all of the film material detaches from its frozen state and fluctuates. The concomitantly increased motion of polymer chains reduces the effective viscosity also for modes with smaller q , which, as a consequence, are sped up and melt in turn. In this way, the film finally melts at all length scales. One might apply this view also to the surface of a bulk polymer sample, for which the spectrum is obtained setting $\alpha = q/2$. As it is readily seen, one should expect surface melting at the polymer surface, down to a thickness of $h_{sm} = h_0 T_g^0 (T_g^0 - T)^{-1}$. To the best of our knowledge, there is yet no conclusive evidence in favour or in disfavour of polymer surface melting. This may be left to further studies.

Let us turn back to our experimental data. From $h_0 = 0.82$ nm, as obtained from the fit, we find for the elastic modulus $E = 44.1$ MPa, which is, on logarithmic scale, right in between the modulus of the frozen material (a few GPa) and the modulus just above T_g (about 300 kPa). As it is well known, both values display no marked dependence on the molecular weight, such that on the basis of our model, $T_g(h)$ is expected as well to be largely independent of molecular weight. This is in agreement with all data collected so far for molecular weights up to about 300 kg/mol. Nevertheless, the exact physical significance of this somewhat arbitrary choice of E , which may be viewed as E at T_g , is to be investigated in further studies.

ACKNOWLEDGMENTS

The authors owe many very helpful hints to J. A. Forrest and K. Dalnoki-Veress. We are furthermore indebted to D. Johannsmann, J. Baschnagel and R. Blossey for stimulating discussions. Funding from the Deutsche Forschungsgemeinschaft within the Priority Program ‘Wetting and Structure Formation at Interfaces’ is gratefully acknowledged.

- [1] J. L. Keddie, R. A. L. Jones, R. A. Cory, *Europhys. Lett.* **27** (1994) 59.
- [2] J. Mattsson, J. A. Forrest, L. Börjesson, *Phys. Rev. E* **62** (2000) 5187.
- [3] J. A. Forrest, K. Dalnoki-Veress, *Adv. Coll. Int. Sci.*, in print.
- [4] P.-G. de Gennes, *Europ. Phys. J. E* **2** (2000) 201.
- [5] K. Dalnoki-Veress, J. A. Forrest, P.-G. De Gennes, J. R. Dutcher, *Journal de Physique IV* (2001), in print.
- [6] J. A. Forrest, J. Mattsson, *Phys. Rev. E* **61** (2000) R53.
- [7] C. Moukarzel, P. M. Duxbury, *Phys. Rev. E* **59** (1999) 2614.
- [8] D. Long, F. Lequeux, submitted to *Europhys. Lett.*
- [9] J. A. Torres, P. F. Nealey, J. J. de Pablo, *Phys. Rev. Lett.* **85** (2000) 3221.
- [10] R. Xie et al., *Phys. Rev. Lett.* **81** (1998) 1251.
- [11] R. Seemann, S. Herminghaus, K. Jacobs *Phys. Rev. Lett.* (2001) in press.
- [12] J. H. Kim, J. Jang, W.-Ch. Zin, *Langmuir* **16** (2000) 4064, and references therein.
- [13] L. D. Landau, E. M. Lifshitz, *Theory of Elasticity* (Vol. **VII**), Butterworth, London 1995.
- [14] L. Landau, Lifshitz, *Hydrodynamics* (Vol. **VI**), Butterworth, London 1995.
- [15] For different boundary conditions, the precise form of the solution changes, and it will be interesting to study whether this corresponds to the observed dependence of the shift of T_g upon the chemical composition of the substrate. However, since the extrapolation length was not characterized in these experiments, this aspect will not be pursued here.
- [16] W. Götzke and L. Sjögren, *Rep. Prog. Phys.* **55** (1992) 241.
- [17] W. Götzke and Th. Vogtmann, *Phys. Rev. E* **61** (2000) 4133.
- [18] The bifurcation behaviour of the particularly simple form emerging here has been discussed, e.g., by E. Leutheusser, *Phys. Rev. A* **29** (1984) 2765.
- [19] P. Hebaud, F. Lequeux, *Phys. Rev. Lett.* **81** (1998) 2934.
- [20] This form is particularly well justified for memory effects in polymers, as it will be shown in a forthcoming paper.

FIG. 1. The glass transition of thin films of 2 kg/mol polystyrene, as determined from thermal expansion (circles) and from the growth of spinodal waves (squares). The solid curve represents our model, which has the elastic modulus governing the dominant modes as its only fitting parameter. It furthermore corresponds to what was found for larger molecular weight PS before [12]. Top: linear scale. Bottom: logarithmic scale, showing more details at small film thickness.